

CRYSTIC[®] GELCOAT 967FR

Fire Retardant Iso - NPG Spray Gelcoat

Introduction

Crystic Gelcoat 967FR is a pre-accelerated, thixotropic Iso -NPG polyester gelcoat. It has been formulated for spray application by an airless machine.

Application

Crystic Gelcoat 967FR has been specially designed for the production of parts in the building and transportation industry where fire retardancy is a key property. It is pre accelerated and only requires the addition of the catalyst to start its curing reaction.

Features and Benefits

Base resin Iso-NPG
Special additives
Fast curing

Excellent chemical & mechanical resistance and flexibility
Improved fire resistance
Fast mould turn round - time saving

Approvals

Crystic Gelcoat 967FR meets M1/F2 fire approval with Crystic 5046 and M2/F2 fire approval with Crystic 26026.

Formulation

Crystic Gelcoat 967FR must be allowed to attain workshop temperature (18-20°C) before use. Stir well by hand or with a low shear mixer and leave for rest. The gelcoat only requires the adding of catalyst to start curing. The recommended catalyst is Butanox M50 (or other equivalent catalyst) which should be added at 2% in the gelcoat.

Geltime

Catalyst level and temperature will influence the geltime. Typical geltime at 25°C of Crystic Gelcoat 967FR for 100 parts gelcoat catalysed with 2 % Butanox M50 is 14-16 minutes.

Recommended Testing

It is recommended that customers test all pigmented gelcoats before use under their own conditions of application to ensure the required surface finish is achieved.

Application

Application Temperature	18 - 20°C
Catalyst	2% Butanox M50
Airless Gun Nozzle	421
Gravity Gun Nozzle	Nozzle 20/10 to 30/10 mm
Pressure	3 to 4.5 bars
Distance to Mould	50cm minimum
Thickness	400 - 600 Microns

Physical Data - Uncured

Property	Unit	Liquid Gelcoat
Viscosity at 25°C	dPas	350 - 400
Index of Thixotropy		6 - 6.5
Specific Gravity at 25°C		1.38
Stability at 20°C	Months	3

Physical Data - Cured

Property	Unit	Fully Cured Base Resin
Barcol Hardness (Model GYZJ 934-1)		45
HDT (1.80 MPa)	°C	90
Elongation at Break	%	2.5
Tensile Strength	MPa	70
Tensile Modulus	MPa	3400

Test according to BS 2782 :1976
1MPa = 1MN/m² = 1N/mm² = 10,2 kgf/cm²

Packaging

Crystic Gelcoat 967FR is supplied in 25Kg kegs and in 200Kg drums.

Storage

Liquid Crystic Gelcoat 967FR should be kept away from heat or flames. It should be stored in its original container and out of direct sunlight. It is recommended that the storage temperature should be less than 20°C. Ideally, containers should be opened immediately prior to use.

Health and Safety

Please see separate Material Safety Data Sheet.

Version 3 : February 2013

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com