



CRESTAKYD[®] 30-8062

Short oil air drying alkyd

INTRODUCTION

Crestakyd 30-8062 is a short oil, quick drying alkyd resin with high hardness.

CHARACTERISTICS

(Not to be taken as a specification)

Appearance		Clear, bit free
Solids content	%	60
Oil type		Linoleic rich
Oil Content	%	38
Solvent		Toluene
Acid Value	mg KOH g ⁻¹	15 max
Viscosity, Brookfield at 25°C, Spindle 3, 20 rpm	mPa·s	1800
Colour	Gardner	6 max

APPLICATIONS

Crestakyd 30-8062 may be used in air drying primers and finishes for metal and wood as well as for road marking paints.

PACKAGING

Crestakyd 30-8062 may be supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

STORAGE

The resin should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 0°C and 30°C. Exposure to direct sunlight should be avoided.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No. 1

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

Scott Bader Company Limited, Wollaston,
Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100
Facsimile: +44 (0) 1933 666529

