



TEXICRYL[®] 13-076

Acrylic copolymer emulsion

INTRODUCTION TEXICRYL 13-076 is an all-acrylic copolymer which has been developed for a variety of coating and binding applications.

CHARACTERISTICS (Not to be taken as a specification)

Solids Content	%	55
Viscosity at 25°C (Brookfield RVT, Spindle 2, 100 rpm)	mPa s	120
pH		9.0
Particle size	nm	250
Specific gravity at 25°C		1.09
Emulsifying system		anion/non-ionic
Minimum film formation temperature*	°C	6
Glass transition temperature	°C	16

* Determined by metal bar with temperature gradient.

APPLICATIONS

TEXICRYL 13-076 is recommended for the formulation of exterior coatings providing excellent water resistance and durability.

TEXICRYL 13-076 can also be used as a polymeric additive in cementitious admixtures, improving physical properties of the system.

PACKAGING

TEXICRYL 13-076 is supplied in drums, 1 tonne IBC's or bulk supplies are delivered by road tanker.

STORAGE

TEXICRYL 13-076 may be stored in the containers in which it is supplied.

Protect from frost and extended exposure to direct sunlight.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No.1

Scott Bader Company Limited
Wollaston, Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

