



TEXICRYL 13-221

Acrylic copolymer emulsion

INTRODUCTION

TEXICRYL 13-221 is self crosslinking acrylic copolymer emulsion designed for textile coatings and non woven applications

CHARACTERISTICS (Not to be taken as a specification)

Solids Content	%	45
Viscosity at 25°C (Brookfield RVT, Spindle 2, 100rpm)	mPa s	100
pH		4.8
Particle Size	nm	250
Minimum film formation temperature*	°C	<2
Glass transition temperature	°C	-15

* Determined by metal bar with temperature gradient.

APPLICATIONS

TEXICRYL 13-221 is designed for the manufacture of non woven materials and enabling good wash resistance properties to be achieved.

PACKAGING

TEXICRYL 13-221 maybe supplied in drums and 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

STORAGE

TEXICRYL 13-221 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No.1

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

Scott Bader Company Limited, Wollaston,
Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100
Facsimile: +44 (0) 1933 666529

