



# TEXICRYL 13-222

## Acrylic copolymer emulsion

### INTRODUCTION

TEXICRYL 13-222 is self crosslinking acrylic copolymer emulsion designed for the manufacture of non woven substrates and textile coating.

### CHARACTERISTICS (Not to be taken as a specification)

Solids Content	%	45
Viscosity at 25°C (Brookfield RVT, Spindle 2, 100rpm)	mPa s	205
pH		4.5
Particle Size	nm	140
Minimum film formation temperature*	°C	<2
Glass transition temperature	°C	11

\* Determined by metal bar with temperature gradient.

**APPLICATIONS**

TEXICRYL 13-222 is used in textile and non woven applications where a medium soft handle is required

**PACKAGING**

TEXICRYL 13-222 maybe supplied in drums and 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

**STORAGE**

TEXICRYL 13-222 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

**HEALTH & SAFETY**

Please see separate Material Safety Data Sheet.

Issue No.1

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

Scott Bader Company Limited, Wollaston,  
Wellingborough, Northamptonshire, NN29 7RL  
Telephone: +44 (0) 1933 663100  
Facsimile: +44 (0) 1933 666529

