



TEXICRYL 13-223

Styrene acrylic copolymer emulsion

INTRODUCTION

TEXICRYL 13-223 is self crosslinking styrene acrylic copolymer emulsion with high solvent and dry clean resistance.

CHARACTERISTICS (Not to be taken as a specification)

| | | |
|---|-------|-----|
| Solids Content | % | 45 |
| Viscosity at 25°C (Brookfield RVT, Spindle 1, 50 rpm) | mPa s | 100 |
| pH | | 6 |
| Particle Size | nm | 210 |
| Minimum film formation temperature* | °C | <2 |
| Glass transition temperature | °C | 11 |

* Determined by metal bar with temperature gradient.

APPLICATIONS

TEXICRYL 13-223 is used in textile and non woven applications where a medium soft handle is required.

PACKAGING

TEXICRYL 13-223 maybe supplied in drums and 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

STORAGE

TEXICRYL 13-223 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No.1

Scott Bader Company Limited
Wollaston, Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

