



TEXICRYL 13-224

Styrene acrylic copolymer emulsion

INTRODUCTION

TEXICRYL 13-224 is self crosslinking styrene acrylic copolymer emulsion with soft handle and good wet scrub resistance properties.

CHARACTERISTICS (Not to be taken as a specification)

Solids Content	%	41
Viscosity at 25°C (Brookfield RVT, Spindle 1, 50 rpm)	mPa s	300
pH		5.5
Particle Size	nm	210
Minimum film formation temperature*	°C	<2
Glass transition temperature	°C	-9

* Determined by metal bar with temperature gradient.

APPLICATIONS

TEXICRYL 13-224 gives excellent binding properties for pigment printing of textiles. It may be used on both rotary and flat frameworks.

PACKAGING

TEXICRYL 13-224 may be supplied in drums and 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

STORAGE

TEXICRYL 13-224 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No.1

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

Scott Bader Company Limited, Wollaston,
Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100
Facsimile: +44 (0) 1933 666529



 INVESTORS
IN PEOPLE