



TEXICRYL[®] 13-307

Carboxylated acrylic copolymer emulsion

INTRODUCTION Texicryl 13-307 is an alkali soluble acrylic emulsion thickener.

CHARACTERISTICS (Not to be taken as a specification)

Solids Content	%	30
Viscosity at 25°C (Brookfield RVT, Spindle 2, 100 rpm)	mPa s	25
Particle size	nm	200
pH		2.5
Specific gravity at 25°C		1.07
Minimum film formation temperature	°C	0
Glass transition temperature	°C	60

APPLICATIONS

Texicryl 13-307 can be used for thickening ceramic tile adhesives when structuring with clays is not appropriate.

PACKAGING

Texicryl 13-307 may be supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

STORAGE

Texicryl 13-307 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No.2

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

Scott Bader Company Limited, Wollaston,
Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100
Facsimile: +44 (0) 1933 666529

