



TEXICRYL 13-308

Carboxylated acrylic copolymer emulsion

INTRODUCTION Texicryl 13-308 is an alkali soluble emulsion designed as a thickener for waterbased formulations

CHARACTERISTICS (Not to be taken as a specification)

Solids Content	%	30.5
Viscosity at 25°C (Brookfield RVT, Spindle 2,100 rpm)	mPa s	25
pH		3
Specific gravity at 25°C		1.07
Minimum film formation temperature*	°C	0
Particle size	nm	200
Glass transition temperature	°C	57

* Determined by metal bar with temperature gradient.

APPLICATIONS Used in the formulation of ceramic tile adhesives, paints and waterborne coating systems.

PACKAGING Texicryl 13-308 is supplied in drums or IBC's. Bulk deliveries are by road tanker.

STORAGE Texicryl 13-308 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH & SAFETY Please see separate Material Safety Data Sheet.

Issue No.3

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

Scott Bader Company Limited, Wollaston,
Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100
Facsimile: +44 (0) 1933 666529

