



TEXICRYL 13-309

Carboxylated acrylic copolymer emulsion

INTRODUCTION

Texicryl 13-309 is a carboxylated acrylic copolymer emulsion designed for use as a thickener in emulsion paints and for thickening various adhesive compounds.

CHARACTERISTICS (Not to be taken as a specification)

Solids Content	%	35
Viscosity at 25°C (Brookfield RVT, Spindle 2, 100 rpm)	mPa s	50
pH		3
Minimum film formation temperature*	°C	10
Glass transition temperature	°C	42

* Determined by metal bar with temperature gradient.

APPLICATIONS

Thickener for use in artist's paints, adhesives and textile coatings. Texicryl 13-309 helps balance rheological properties of a paint and aids application / flow properties.

PACKAGING

Texicryl 13-309 may be supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

STORAGE

Texicryl 13-309 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No. 3

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

Scott Bader Company Limited, Wollaston,
Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100
Facsimile: +44 (0) 1933 666529

