



TEXICRYL 13-527

Styrene acrylic copolymer emulsion

INTRODUCTION Texicryl 13-527 is a high performance styrene acrylic copolymer emulsion designed for use in cold seal adhesive applications.

CHARACTERISTICS (Not to be taken as a specification)

Solids Content	%	50
Viscosity at 25°C (Brookfield RVT, Spindle 2, 20 rpm)	mPa s	90
pH		6.5
Minimum film formation temperature*	°C	26
Glass transition temperature	°C	25

* Determined by metal bar with temperature gradient.

APPROVALS FDA 176.180
BfR XIV

APPLICATIONS Cold seal adhesives.

PACKAGING Texicryl 13-527 is supplied in 1 tonne IBC's. Bulk deliveries are by road tanker.

STORAGE Texicryl 13-527 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH & SAFETY Please see separate Material Safety Data Sheet.

Issue No.1

Scott Bader Company Limited
Wollaston, Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

