



# TEXICRYL 13-528

## Styrene acrylic copolymer emulsion

### INTRODUCTION

Texicryl 13-528 is a high performance styrene acrylic copolymer emulsion designed for use in cold seal adhesive applications.

### CHARACTERISTICS (Not to be taken as a specification)

Solids Content	%	50
Viscosity at 25°C (Brookfield RVT, Spindle 2, 20 rpm)	mPa s	100
pH		6.5
Minimum film formation temperature*	°C	10
Glass transition temperature	°C	9

\* Determined by metal bar with temperature gradient.

### APPROVALS

FDA 175.105  
FDA 176.170  
FDA 176.180  
BfR XIV

## APPLICATIONS

Cold seal adhesives

## PACKAGING

Texicryl 13-528 is supplied in 1 tonne IBC's. Bulk deliveries are delivered by road tanker.

## STORAGE

Texicryl 13-528 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

## HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No.1

Scott Bader Company Limited  
Wollaston, Wellingborough, Northamptonshire, NN29 7RL  
Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

INVESTOR IN PEOPLE

