



# TEXICRYL 13-602

## Styrene acrylic copolymer emulsion

**INTRODUCTION** Texicryl 13-602 is a styrene acrylic copolymer emulsion designed for use in flexible fillers and caulks.

**CHARACTERISTICS (Not to be taken as a specification)**

Solids Content	%	50
Viscosity at 25°C (Brookfield RVT, Spindle 3, 50 rpm)	mPa·s	1000
pH		8
Minimum film formation temperature*	°C	20
Glass transition temperature	°C	20

\* Determined by metal bar with temperature gradient.

**APPLICATIONS**

Flexible fillers, caulks and sealant applications

**PACKAGING**

Texicryl 13-602 maybe supplied in drums or IBC's (please check with your local representative) . Bulk deliveries are by road tanker.

**STORAGE**

Texicryl 13-602 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

**HEALTH & SAFETY**

Please see separate Material Safety Data Sheet.

Issue No. 2

Scott Bader Company Limited  
Wollaston, Wellingborough, Northamptonshire, NN29 7RL  
Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

