



# TEXICRYL 13-608

## Acrylic copolymer emulsion

### INTRODUCTION

TEXICRYL 13-608 is a high performance acrylic copolymer emulsion designed for use in exterior coating applications.

### CHARACTERISTICS (Not to be taken as a specification)

Solids Content	%	50
Viscosity at 25°C (Brookfield RVT, Spindle 2, 50 rpm)	mPa s	75
pH		8.0
Particle Size	nm	200
Minimum film formation temperature*	°C	20
Glass transition temperature	°C	28

\* Determined by metal bar with temperature gradient.

## APPLICATIONS

High performance exterior coatings with excellent adhesion, durability and UV resistance

## PACKAGING

TEXICRYL 13-608 maybe supplied in drums and 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

## STORAGE

TEXICRYL 13-608 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

## HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No.1

Scott Bader Company Limited  
Wollaston, Wellingborough, Northamptonshire, NN29 7RL  
Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

