



TEXICRYL[®] 17-0376

Modified styrene acrylic copolymer

INTRODUCTION **TEXICRYL 17-0376** is a modified styrene acrylic copolymer emulsion designed for use in high performance anticorrosive primers.

Start point formulas available.

CHARACTERISTICS **(Not to be taken as a specification)**

Solids content	%	45 - 47
Viscosity at 25°C (Brookfield RVT, Spindle 2, 20 rpm)	cps	150 – 2000
pH	-	8.2 – 9.2
Particle size	nm	70 - 135
Relative density at 25°C		1.05
Emulsifying System		Anionic
MFFT*	°C / °F	17 / 63
Tg	°C / °F	7 / 19

**Determined by metal bar with temperature gradient.*

APPLICATIONS **TEXICRYL 17-0376** has been specifically designed for the formulation of low VOC waterbased anticorrosive primers which provide excellent salt spray (to ASTM B117), humidity and prohesion resistance on clean metal substrates. Correctly formulated primers based on **TEXICRYL 17-0376** show good mechanical properties along with improved UV and heat resistance in comparison to those based on halogen containing polymers.

TEXICRYL 17-0376 is Alkyl Phenol Ethoxylate free.

For more information please ask for a copy of the Industrial Coatings Notebook.

PACKAGING

TEXICRYL 17-0376 is supplied in a 460 lb. net weight plastic drum.

STORAGE

TEXICRYL 17-0376 can be stored in the containers in which it is supplied.

Protect from temperatures below 40°F.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

3/06

NOTICE

The information and recommendations in this publication are, to the best of our actual knowledge, reliable. Suggestions made concerning uses or applications are only the opinion of Scott Bader, Inc. and users of these products should make their own tests to determine the suitability of these products for their own particular purposes. Because of numerous factors beyond our control affecting the results of the use of these products, SCOTT BADER, INC. MAKES NO WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, OTHER THAN THAT THE PRODUCT CONFORMS TO IT'S APPLICABLE CURRENT STANDARD SPECIFICATION.

Suggestions for uses of our products should not be understood as recommending the use of our products in violation of any patent.

7/04