



TEXICRYL[®] S-09

INTRODUCTION

TEXICRYL S-09 is an alkali-soluble styrene acrylic resin developed for water-based coatings and inks.

The resin is supplied in solid form, and is designed to impart gloss and resolubility to water-based coatings within the graphic arts market.

CHARACTERISTICS (Not to be taken as a specification)

Appearance		solid clear flakes
Solids Content	%	97
Specific gravity (at 25°C)		1.12
pH		8.5
Acid value	mg KOH/g ⁻¹	220
Molecular weight		9,500
Glass transition temperature	°C	105

APPLICATIONS

TEXICRYL S-09 is readily let down, at elevated temperature in water, in the presence of Ammonia or other suitable amine. Solutions of the resin must be kept at all times above pH 7, otherwise the resin will tend to revert back to its solid form.

The solid resin form / geometry is designed to give rapid solubility when made up into solutions.

The solids content of resin solutions based on TEXICRYL S-09 should be made up at around 30-35% in order to give optimum pigment grinding capability and in the case of clear coatings, maximum solids to give the highest achievable film build. Yet at this level of solids the resin solution will still flow easily and be pump-able.

In the resin solution form, TEXICRYL S-09 may be used as a let-down solution to clear coatings (OPV's) and inks. Resin solutions are designed to be compatible with all components commonly used in formulation graphic arts compounds, including the range of TEXICRYL emulsions designed for the graphic arts market, as well as surfactants, additives waxes alcohols and solvents.

TEXICRYL S-09 will impart gloss and resolubility to systems, yet maintaining low foaming and contributing to good printability.

PACKAGING

TEXICRYL S-09 is supplied in opaque polyethylene sacks. Net weight 20 kg per sack; 50 sacks per shrink-wrapped pallet.

STORAGE

Store away from heat source.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No.1

Scott Bader Company Limited
Wollaston, Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

INVESTOR IN PEOPLE

