



# TEXIPOL<sup>®</sup> 63-303

## High Solids Inverse Emulsion Polymer

### INTRODUCTION

Texipol 63-303 is a high efficiency inverse emulsion thickener for use in a wide range of water based formulations.

### CHARACTERISTICS (Not to be taken as a specification)

Appearance		Creamy liquid
Viscosity at 25°C (Brookfield RVT, Spindle 3, 20rpm)	mPa s	3000
1.25% aqueous solution viscosity (Brookfield RVT, Spindle 6,5rpm)	mPa s	75000
1.25% aqueous solution pH		6.5
Specific gravity at 25°C		1.05

**APPLICATIONS**            Thickening PVA bonding aid, construction and industrial adhesives

**PACKAGING**            Texipol 63-303 is supplied in drums and IBC's.

**STORAGE**                Texipol 63-303 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided. Do not store in mild steel , Copper or Aluminium containers

**HEALTH & SAFETY**    Please see separate Material Safety Data Sheet.

Issue No.1

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

Scott Bader Company Limited, Wollaston,  
Wellingborough, Northamptonshire, NN29 7RL  
Telephone: +44 (0) 1933 663100  
Facsimile: +44 (0) 1933 666529

