



Speciality Polymers

TEXIPOL[®] 63-237

Provisional Data Sheet

INTRODUCTION

TEXIPOL 63-237 is a multifunctional inverse emulsion thickener which Scott Bader have developed specifically for the pigment printing of textiles. TEXIPOL 63-237 is supplied as a low viscosity, easy to use inverse emulsion which, if required, can easily be pumped and metered. The polymer in TEXIPOL 63-237 is already in solution, therefore thickening of printing paste formulations is almost instantaneous. Pigment printing formulations can be effectively thickened by the direct addition of TEXIPOL 63-237 to the mix, or by following the conventional method of preparing a thickener stock. TEXIPOL 63-237 is a suitable thickener for pigment printing of cotton, polyester, blended fabrics or other fibrous material. Texipol 63-237 is Alkyl Phenol Ethoxylate free.

CHARACTERISTICS

(Not to be taken as a specification)

Appearance	Creamy liquid
Specific Gravity at 25°C	~1.05
Inverse emulsion viscosity Brookfield RVT, Spindle 7, 100 rpm at 25°C	4,500 mPa s
Thickened deionised water*	38,000 mPa s
Flow of thickened compositions	Extremely short
Polymer charge	Anionic
Polymer compatibility	Anionic/non-ionic
Flash point	100°C

* Deionised water thickened with 2% of TEXIPOL 63-237 as supplied. Brookfield RVT, Spindle 6, 5 rpm at 25°C.

BENEFITS

Sharper and better defined prints.
Superior fastness dry and wet, colour brightness, colour yield & handling.
Easy to use compared to powders and non-dispersed gels.
Instantly modifies the Rheology and viscosity of the printing paste formulations.

Can be added directly to printing pastes. Effective in use over a wide pH range.

Does not require the use of any other additives such as ammonia, surfactant, activator, promoter, etc. No significant odour.

Texipol 63-237 is Alkyl Phenol Ethoxylate free.

APPROVALS

TEXIPOL 63-237 is suitable for use in Öko-Tex applications.

APPLICATIONS

Suggested applications include the use of Texipol 63-237 for thickening pigment printing pastes for printing cotton, polyester, blended fabrics and other fibrous materials. TEXIPOL 63-237 can be used for preparing a thickener stock with or without other additives, except colour. When covered adequately [preferably in the absence of air], thickened stock can be stored for long periods, without any signs of skin formation. In another method, Texipol 63-237 is added to the stirring mixture of pre-weighed water, pigment and binder and other ingredients of the printing paste formulation. Thickening is normally achieved in less than 1 minute, but the optimum thickening time might vary according to stirrer efficiency and formulation ingredients.

A typical formulation is TS2822.

Thickened paste has a viscosity of >30,000 mPas, (Brookfield RVT,

Spindle 6, Speed 5 at 25°C) and pH of ~8.5. Other chemicals, such

as preservatives, humectants, antifoams, softeners, definition

improvers, etc, if required can also be added to the print paste

formulations, preferably before the addition of TEXIPOL 63-237.

TEXIPOL 63-237 is suitable for printing using handscreens, rotary and flat bed printing machines.

PACKAGING

TEXIPOL 63-237 is supplied in 120 kg polyethylene open-topped kegs, 200 kg lacquer-lined open-topped drums and 1000 kg tanks and 100 kilo polyethylene kegs.

STORAGE

TEXIPOL 63-237 may be stored at temperatures between 5° - 40°C. If the product freezes it should be thawed completely by placing the container in a warm water bath and homogenised completely by mixing thoroughly before use.

TEXIPOL 63-237 can be stored in glass, stainless steel, plastic or epoxy lined vessels. It should not be stored in mild steel, copper or aluminium containers.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No. 2.1 SA Sep 2005

SCOTT BADER (Pty) Ltd
Reg. No. 93/00466/07
1 Lubex Road, Hammarsdale
P.O. Box 1539, Hillcrest, 3650
South Africa
Telephone: +27 (0) 31 736 8500
Telefax: +27 (0) 31 736 8511

Gauteng
11 Belgrade Avenue
Aeroporto, Spartan Ext.2
Kempton Park
Tel: (011) 974 7104
Fax: (011) 974 1300

KwaZulu Natal
Unit 5, Pastel Park,
Wareing Road
Pinetown
Tel: (031) 709 3879
Fax: (031) 709 3887

Eastern Cape
134 Paterson Road
Northend
Port Elizabeth
Tel: (041) 487 2060
Fax: (041) 487 7917

Western Cape
4 Beverly Road
Montague Gardens
Cape Town
Tel: (021) 552 0970
Fax: (021) 552 1031

