




# TEXIPOL 67-5055


High Efficiency Inverse Emulsion Thickener  
for Chromojet\* Printing Machinery



\* Chromojet is a trademark of J. Zimmer, Maschinenbau GmbH (Austria).

# TEXIPOL 67-5055

Texipol® 67-5055 is a high efficiency inverse emulsion thickener specifically designed for Chromojet printing. Inverse emulsions differ from conventional emulsions in that they are water in oil emulsions whereas conventional emulsions are the opposite i.e oil in water. This is shown in the diagram below:



## Benefits of Texipol 67-5055 Inverse Emulsion Technology

- Low viscosity compared to conventional water soluble polymers – easy to pump and meter e.g. can use Supramix system (supplied by J.Zimmer Maschinenbau GmbH, Austria).
- Excellent storage stability with minimal separation and wastage.
- Preneutralised meaning thickening of printing pastes is almost instantaneous and no alkali is needed.
- Specifically designed for jet printing giving sharp well defined prints with excellent colour yield, brightness and handle.
- No jet blocking due to the carefully selected solubility characteristics of the copolymer.

Thus, specialised inverse emulsion manufacturing technology has enabled the manufacture of polymers with optimum performance characteristics and ease of transport, handling, storage and user benefits.

## Multifunctional Inverse Emulsions in Chromojet Printing

In general terms the thickener has 2 functions to fulfil in a typical formulation:

- To increase the viscosity to the desired level for printing.
- To modify the flow to ensure optimal printing characteristics.

Additionally the inverse emulsion thickener delivers further benefits:

- Acid donor during fixation.
- Humectant, thus improving the fixation in the steamer.

# Start Point Formulations for ChromoJet Printing

The following formulations have been put together to offer the ChromoJet user a start-point for the printing of various carpet substrates. Further work will be required to optimise the finish of the printed carpet depending on individual company requirements and quality standards. The Scott Bader applications group will be happy to assist in formulation optimisation by carrying out trials either at the customer premises or at Scott Bader's headquarters using our own printing facilities.

## Formulation Notes

- Scott Bader recommends that a stock paste is used when formulating dye pastes for ChromoJet printing. Typical levels of Texipol 67-5055 are around 17 – 20 grams per litre either directly or via SupraMix system.
- For ease of understanding, the start point formulations are presented in a 1000 part format.
- No specific viscosities are given as this will vary depending on carpet type. Texipol 67-5055 works at all viscosities used with ChromoJet printing (50 - 600 cps, Haake/RION typically).
- Dyestuff quantities will depend on customer requirements. Texipol 67-5055 is compatible with all concentrations.

## Polyamide

Raw Material	Quantity
Water	Make up to 1000 part
Texipol 67-5055	5.00 – 12.00
Acid/Metal complex dyestuff	0.20 – 3.00

**Notes:** Typical pH between 5.0 – 5.5

## Cotton and Viscose (Cellulosics)

Raw Material	Quantity
Water	Make up to 1000 parts
Texipol 67-5055	10.00 – 12.00
Direct/Reactive dyes	0.20 – 3.00
Sodium Chloride	4.00
Sodium Hydroxide (33%)	Adjust to pH 11 - 12

**Notes:** The addition of sodium chloride will reduce the viscosity of the print paste. When adjusting the pH to 11 – 12, the viscosity will increase. A small amount of work is required to find the optimum quantity of ingredients to achieve the desired viscosity in the pH range.


## Wool


Raw Material	Quantity
Water	Make up to 1000 part
Texipol 67-5055	5.00 – 12.00
Acid/Metal complex dyestuff	0.20 – 3.00
Citric Acid	Adjust to pH 4.0 – 4.5

**Notes:** Printing wool at pH 4.0 – 4.5 produces carpet of superior colour brilliancy.

## Acrylic

Raw Material	Quantity
Water	Make up to 1000 part
Texipol 67-5055	5.00 – 10.00
Basic Dyes	0.20 – 3.00





## Scott Bader Group of Companies

United Kingdom

### Scott Bader Company Limited

Tel: +44 1933 663100 Fax: +44 1933 666529  
email: [specpol@scottbader.com](mailto:specpol@scottbader.com)

France

### Scott Bader SA

Tel: +33 3 22 66 27 66 Fax: +33 3 22 66 27 80  
email: [specpol@scottbader.fr](mailto:specpol@scottbader.fr)

UAE

### Scott Bader Middle East Ltd

Tel: +971 48835025 Fax: +971 48835319  
email: [info@scottbader.co.ae](mailto:info@scottbader.co.ae)

P.R. China

### Scott Bader Asia Pacific

Tel: +86 21 529 87778 Fax: +86 21 529 88889  
email: [info@scottbader.cn](mailto:info@scottbader.cn)

USA

### Scott Bader Inc

Tel: +1 330 920 4410 Fax: +1 330 920 4415  
email: [info@scottbaderinc.com](mailto:info@scottbaderinc.com)

---

### Commercial contact:

Didier Benoit, Textile Industry Manager,  
email: [didier\\_benoit@scottbader.com](mailto:didier_benoit@scottbader.com)


### Technical contact:

Mark Stanion, Senior Applications Chemist,  
email: [mark\\_stanion@scottbader.com](mailto:mark_stanion@scottbader.com)



# SCOTT BADER

## Speciality Polymers



[www.scottbader.com](http://www.scottbader.com)



INVESTOR IN PEOPLE

**All information is given in good faith but without warranty.  
We cannot accept responsibility or liability for any damage,  
loss or patent infringement resulting from the use of this information.**

