

Crystic Fireguard Topcoat 72PAX

Fire Retardant Spray Topcoat

Introduction

Crystic Fireguard Topcoat 72PAX is a pre-accelerated filled spray topcoat. It is available in a wide range of colours and the information contained in this technical data sheet also applies to these pigmented versions.

Applications

Crystic Fireguard Topcoat 72PAX can be used both internally and externally for building, transport and general industrial work.

Features and benefits

Crystic Fireguard Topcoat 72PAX has very low flammability.

Formulation

Crystic Fireguard Topcoat 72PAX should be allowed to attain workshop temperature (18°C-20°C) before use. Stir well by hand or with a low shear stirrer to avoid aeration and then allow to stand to regain thixotropy. Crystic Fireguard Topcoat 72PAX requires only the addition of catalyst to start the curing reaction. The recommended catalyst is Butanox M50 (or other equivalent catalyst) which should be added at 2% into the topcoat. (Please consult our Technical Service Department if other catalysts are to be used). The catalyst should be thoroughly incorporated into the topcoat, with a low shear mechanical stirrer where possible.

Spray Application

Do

- Gently stir the topcoat before use by hand or low shear stirrer.
- Ensure the topcoat has attained workshop temperature of 18°C-25°C before use. (Temperatures below 18°C will require higher pressure to achieve an acceptable spray pattern and this will encourage porosity).
- Spray at the minimum practical pressure whilst maintaining an acceptable spray pattern and full fan width.
- Apply a mist coat and then build up thickness in long, even passes until the recommended wet film thickness of 0.4-0.5mm (0.015-0.020 inch) is reached. This will minimise porosity and colour defects.

Don't

- Stir the topcoat with high shear mixers as this will temporarily break down the thixotropy leading to drainage.
- Exceed a wet film thickness of 0.625mm (0.025 inch) as thick films encourage air retention.
- Apply excessive thickness in corner areas as this can cause pre-release.

Additives

The addition of fillers or pigments to Crystic Fireguard Topcoat 72PAX is likely to affect the weathering and cure of this material and is not recommended.

Recommended Testing

It is recommended that customers test Crystic Fireguard Topcoat 72PAX before use under their own conditions of application to ensure the required surface finish is achieved.

Typical Properties

The following tables give typical properties of Crystic Fireguard Topcoat 72PAX when tested in accordance with SB, BS EN or BS EN ISO test methods.

Property	Unit	Liquid
Appearance		Opaque, coloured
Viscosity at 25°C		Thixotropic
Specific Gravity at 25°C		1.40
Volatile Content	%	32
Stability at 20°C	months	3
Gel time at 25°C using 4% Accelerator E and 2% Butanox M50 (or other equivalent catalyst)	minutes	6 -10

Property	Unit	Fully cured* topcoat (unfilled casting)
Barcol Hardness (Model GYZJ 934-1)		54
Deflection Temperature under load† (1.80 MPa)	°C	80
Elongation at Break	%	2
Tensile Strength	MPa	55
Tensile Modulus	MPa	5200

*Curing Schedule - 24hrs @ 20°C, 3hrs @ 80°C

† Curing Schedule - 24hrs @ 20°C, 5hrs @ 80°C, 3hrs @ 120°C

Post Curing

For many applications, Crystic Fireguard Topcoat 72PAX will perform adequately when cured at workshop temperature (20°C). However, for optimum properties it should be allowed to cure for 24 hours at 20°C, and then be oven-cured for 3 hours at 80°C.

Storage

Crystic Fireguard Topcoat 72PAX should be stored in its original container and out of direct sunlight. It is recommended that the storage temperature should be less than 20°C where practical, but should not exceed 30°C. Ideally, containers should be opened only immediately prior to use.

Packaging

Crystic Fireguard Topcoat 72PAX is supplied in 25 kg and 225 kg containers.

Health and safety

Please see separate Material Safety Data Sheet.

Version 2: February 2013

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com