

CRYSTIC[®] 272

Tough, Resilient Isophthalic Polyester Resin

Introduction

Crystic 272 is an isophthalic unsaturated polyester resin. It is recommended for use in high performance applications using filament winding, pultrusion, and centrifugal or contact moulding methods. The outstanding wetting characteristics of the resin make it particularly suitable for use with continuous rovings, carbon fibre and Kevlar[®]. Fully cured laminates made with Crystic 272 have high mechanical strength and excellent strength retention in wet environments, at temperatures up to 60°C.

Approvals

Crystic 272 carries the SANS 713:2007 mark.

Formulation

Crystic 272 can be used in hot, heat-assisted and cold curing formulations by using the following recommended catalyst systems.

Benox[®] C50 for hot curing.

Benox C50 and Norox[®] CHP for heat-assisted curing.

Norox[®] KP9, or

Norox[®] MEKP-925H for cold curing.

Hot Curing

Benox C50 should be added at 2% and thoroughly dispersed in the resin. The catalysed mix will remain usable for approximately 5 days at workshop temperature (18°C-25°C). Cure will take place between 80°C and 140°C, but for most applications, 120°C will be satisfactory. Approximate gellimes are shown in the Table 1, which should be used as a guide only, not as a specification.

Table 1: Approximate hot curing gellime for Crystic 272.

Temperature	Setting Time in Minutes
80°C	8
100°C	4
120°C	2

Heat-Assisted Curing

Benox C50 and Norox CHP should be added at 1% and thoroughly dispersed in the resin. Shortly before use, the correct amount (1% - 4%) of Crystic Accelerator E should be stirred into the resin. This mix will remain usable at workshop temperature (18°C - 25°C) for 6 to 24 hours. Gelation will take place at 60°C and above, making this formulation particularly suitable for winding and drawing applications, which require a long pot life.

Cold Curing

Norox KP9 should be added at 2% into the resin. For taint free laminates, to be used with foodstuffs, 2% Norox MEKP-925H should be used. The catalyst must be thoroughly dispersed in the resin, and this mix will remain usable for approximately 8 hours at workshop temperature (18°C-20°C). Shortly before use, the correct amount (1%-4%) of Crystic Accelerator E should be stirred into the catalysed resin.

Additives

Crystic 272 may be pigmented by the addition of up to 5% Crystic Pigment Paste. The addition of certain pigments, fillers or extra styrene may adversely affect the food taint, toxicity and chemical resistant properties of Crystic 272. Users should therefore satisfy themselves that any additions made would give the performance required.

N.B. Peroxide catalysts are highly reactive and may decompose with explosive violence, or cause fires, if they come into contact with flammable materials, metals or accelerators. For this reason they must never be stored in metal containers or be mixed directly with accelerators.

Chemical Resistance

Performance figures for fully cured Crystic 272 laminates, in more than 200 chemical environments, are shown in Technical Leaflet No. 145 "Safe Chemical Containment".

Post Curing

Satisfactory laminates for many applications can be made with Crystic 272 by curing at workshop temperature (25°C). However, for optimum chemical, water and heat resistant properties, heat-assisted and cold cured laminates must be post cured before being put into service. Mouldings should be allowed to cure for 24 hours at 25°C and then be oven cured for 3 hours at 80°C.

Post curing is not normally necessary for hot cured laminates provided that the moulding cycle is adequate.

Mouldings that are to be used with foodstuffs should be allowed to cure for 24 hours at 25°C and then be oven cured for a minimum of 3 hours at 85°C. They should be thoroughly wet-steam cleaned for at least one hour prior to use. If wet-steam cleaning is not practical, suitably shaped mouldings can be filled with hot water (60°C - 80°C) containing non-perfumed detergent. After 2 hours, they should be emptied and thoroughly rinsed with several batches of clean hot water. These precautions are essential to avoid the tainting of foodstuffs.

Typical Properties

The following tables give typical properties of Crystic 272 when tested in accordance with SANS 713-2007.

Table 3: Typical properties of Crystic 272 Liquid Resin

Property	Units	Nominal value
Appearance		Clear, yellowish liquid
Viscosity @ 25°C 37.35 sec ⁻¹	centipoise	360
Density @ 25°C	g/cm ³	1.10
Volatile Content	%	41
Acid Value	mg KOH/g	18
Stability in the dark @ 20°C	months	6
Geltime @ 25°C using 2% Norox KP9 and 2% Crystic Accelerator E	minutes	12

Table 4: Typical properties of Crystic 272 Fully Cured* Resin (unfilled casting)

Property	Units	Nominal value
Barcol Hardness (Model GYZJ 934-1)		43
Deflection Temperature under load (1.80 MPa) †	°C	66
Water Absorption 7 days at 23°C	mg	55
Tensile Strength	MPa	79
Tensile Modulus	MPa	3400
Elongation at Break	%	3.6 minimum

* Curing Schedule - 24 hrs at 20°C, 3 hrs at 80°C

† Curing schedule - 24hrs @ 20°C, 5hrs @ 80°C, 3hrs @ 120°C



Storage

Crystic 272 should be stored in the dark in suitable, closed containers. It is recommended that the storage temperature should be less than 20°C where practical, but should not exceed 30°C. Ideally, containers should be opened only immediately prior to use. Where they have to be stored outside, it is recommended that drums be kept in a horizontal position to avoid the possible ingress of water. Wherever possible, containers should be stored under cover.

Packaging

Crystic 272 is supplied in 25kg kegs, 225kg drums, and 1125kg intermediate bulk containers. Bulk supplies can be delivered by road tanker.

Health and Safety

Please see the applicable Material Safety Data Sheets, depending on the curing system used.

Technical Leaflet No 102.22SA
August 2013

Before you use this information, kindly verify that this data sheet is the latest version.

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

SCOTT BADER COMPANY LIMITED

Scott Bader (Pty) Ltd
Reg. No. 93/00466/07
1 Lubex Road,
Hammarsdale
P.O. Box 1539, Hillcrest,
3650. South Africa
Tel: +27 (0) 31 736 8500
Fax: +27 (0) 31 736 8511

Gauteng
Broadacres Business
Centre
Cnr Cedar Rd and 3rd
Ave
Broadacres, Sandton
Tel: (011) 064 5673

KwaZulu Natal
1 Lubex Road,
Hammarsdale
Tel: (031) 736 8500

Eastern Cape
Freightpak Building
Chevrolet St
Markman Industrial
Port Elizabeth
Tel: (041) 409 783

Western Cape
Unit 4B
Tyger Lake
Niagara Way
Tyger Valley
Cape Town
Tel: (021) 914 6011

