

CRYSTIC[®] PD 9453PA

Fire Retardant Polyester Resin for Resin Transfer Moulding

Introduction

Crystic PD 9453PA is a pre-accelerated, filled polyester resin designed for use in RTM.

Applications

Crystic PD 9453PA is suitable for use in the building and land transport industries, and for general RTM and Vacflo applications.

Features & Benefits

The viscosity characteristics of Crystic PD 9453PA have been designed to facilitate flow through the mould, while minimising filler settlement during storage.

Approvals

Fully cured laminates moulded with Crystic PD 9453PA can obtain a Class 1 rating to B.S. 476 Part 7: 1987.

Product Characteristics

Formulation

Crystic PD9453PA must be thoroughly stirred and allowed to attain workshop temperature (18°C - 20°C) before use. It needs only the addition of a catalyst to start the curing reaction. The recommended catalyst is Trigonox 44B which should be added at 1-2% into the resin. The geltime of Crystic PD9453PA can be approximately determined from the table below.

Pot Life

Temperature	Pot life in minutes using Trigonox 44B		
	1.0	1.5	2.0
20°C	-	-	20
25°C	-	-	13
40°C	5	4.5	4
50°C	-	-	2

The resin, mould and workshop should be at, or above, 15°C before curing is carried out.

Additives

Crystic PD 9453PA can be supplied in a restricted range of colours. This eliminates the potential for mixing errors with small quantities of Pigment Paste. The addition of Pigment Paste to Crystic PD 9453PA is not recommended due to the difficulty in obtaining specific colours. The addition of any pigment or other additives may adversely affect the resin transfer moulding process and the properties of the cured laminate. Users should consult Scott Bader's Technical Service Department before making any such additions.

Post Curing

Satisfactory laminates for many applications can be made from Crystic PD9453PA by curing at workshop temperature (20°C). For optimum properties, however, laminates should be post-cured before being put into service. The laminate should be allowed to cure for 24 hours at 20°C, and then be oven cured for 16 hours at 40°C or 3 hours at 80°C.

Typical Properties

The following tables give typical properties of Crystic PD 9453PA when tested in accordance with the appropriate BS or BS EN ISO test method.

Property		Liquid resin
Appearance		Pinkish white
Viscosity at 25°C	Poise	1.7
Specific gravity at 20°C		1.48
Volatile content	%	76
Stability in the dark at 25°C	Months	3
Geltime at 25°C using 2% Trigonox 44B	Minutes	13

Property		Fully cured* resin (unfilled casting)
Barcol hardness (GYZJ 934 - 1)		50
Deflection temperature under load † (1.80 MPa)	°C	80
Water Absorption 24hrs @ 23°C	mg	17
Tensile strength	MPa	41
Tensile modulus	MPa	4050
Elongation at break	%	1.45

* Curing Schedule - 24hrs @ 20°C, 3hrs @ 80°C

† Curing Schedule - 24hrs @ 20°C, 5hrs @ 80°C, 3hrs @ 120°C

Property		**Laminate
Glass content	%	14.5
Tensile strength	MPa	67
Tensile modulus	MPa	5425
Elongation at break	%	1.9
Flexural strength	MPa	164
Flexural modulus	MPa	6650
Notched Izod impact	kJ/m ²	104
Charpy impact	kJ/m ²	41

** Made with 1 layer Rovicore 600 D3 600

Curing Schedule - 24hrs @ 20°C, 3hrs @ 80°C

Storage

Crystic PD 9453PA should be stored in the dark in suitable closed containers. It is recommended that the storage temperature should be less than 20°C where practical, but should not exceed 30°C. Ideally, containers should be opened only immediately prior to use.

Packaging

Crystic PD 9453PA is supplied in 225kg steel containers.



Health & Safety

Please see separate Materials Safety Data Sheet.

Technical Leaflet No 102.22SA
August 2013

Before you use this information, kindly verify that this data sheet is the latest version.

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

SCOTT BADER COMPANY LIMITED

Scott Bader (Pty) Ltd
Reg. No. 93/00466/07
1 Lubex Road,
Hammasdale
P.O. Box 1539, Hillcrest,
3650. South Africa
Tel: +27 (0) 31 736 8500
Fax: +27 (0) 31 736 8511

Gauteng
Broadacres Business
Centre
Cnr Cedar Rd and 3rd
Ave
Broadacres, Sandton
Tel: (011) 064 5673

KwaZulu Natal
1 Lubex Road,
Hammasdale
Tel: (031) 736 8500

Eastern Cape
Freightpak Building
Chevrolet St
Markman Industrial
Port Elizabeth
Tel: (041) 409 783

Western Cape
Unit 4B
Tyger Lake
Niagara Way
Tyger Valley
Cape Town
Tel: (021) 914 6011

