

# CRYSTIC<sup>®</sup> Gelcoat 44PA

## Sandable Spray Gelcoat

### Introduction

Crystic Gelcoat 44PA is a pre-accelerated, isophthalic, filled, sandable gelcoat. It has been specifically designed for applications that are to be post-painted. Crystic Gelcoat 44PA has been formulated for spray application.

The gelcoat is available in a limited range of colours and the information contained in this leaflet also applies to these pigmented versions.

### Formulation

Crystic Gelcoat 44PA should be allowed to attain workshop temperature (18-25°C) before use. Stir well by hand, or with a low shear mixer to avoid aeration, and then allow to stand to regain thixotropy. The product requires only the addition of catalyst to start the curing reaction. The recommended catalyst is Norox<sup>®</sup> KP-9 or Norox<sup>®</sup> MEKP-925 H, which should be added at 2% into the gelcoat. (Please consult our Technical Service Department if other catalysts are to be used). The catalyst should be thoroughly incorporated into the gelcoat, with a low shear mechanical stirrer, where possible. Unsaturated polyester products release heat when they cure in bulk. If manually adding catalyst to the product prior to spraying, do not prepare more material than is required to complete the job and spray within 3 minutes. Ensure that all equipment is thoroughly cleaned after use.

### Pot Life

Temperature	Pot Life in Minutes
25°C	6

Curing should not be carried out at temperatures below 15°C. The gelcoat, mould and workshop should all be at, or above, this temperature.

N.B. Peroxide catalysts are highly reactive and may decompose with explosive violence, or cause fires, if they come into contact with flammable materials, metals or accelerators. For this reason they must never be stored in metal containers or be mixed directly with accelerators.

### Additives

Crystic Gelcoat 44PA is supplied in a limited range of colours. This eliminates the potential for mixing errors with small quantities of pigment paste. The gelcoat is filled, so the addition of further quantities of filler, or pigments, may adversely affect the properties of both liquid and cured gelcoats.

### Post Curing

Satisfactory laminates for many applications can be made with this gelcoat by curing at workshop temperature (25°C).

### Application

For normal moulding, the application of Crystic Gelcoat 44PA should be controlled to 0.4-0.5 mm (0.015-0.020 inch) wet film thickness. As a guide, approximately 450-600 g/m<sup>2</sup> of gelcoat mixture (depending on pigment) will give the required thickness when evenly applied.

### Do

- Gently stir the gelcoat before use by hand or low shear mixer.
- Ensure the gelcoat has attained workshop temperature of 18°C-25°C before use. (Temperatures below 18°C will require higher pressure to achieve an acceptable spray pattern and this will encourage porosity).
- Spray at the minimum practical pressure whilst maintaining an acceptable spray pattern and full fan width.
- Apply a mist coat and then build up thickness in long, even passes of 0.125mm (0.005 inch) until the recommended wet film thickness of 0.5-0.625mm (0.020-0.025 inch) is reached. This will minimise porosity and colour defects.

**Don't**

- Stir the gelcoat with high shear mixers as this will temporarily break down the thixotropy leading to drainage.
- Exceed a wet film thickness of 0.625mm (0.025 inch) as thick films encourage air retention.
- Apply excessive thickness in corner areas as this can cause pre-release.

**Typical Properties**

The following tables give typical properties of Crystic Gelcoat 44PA when tested in accordance with BS2782:

Property		Liquid Gelcoat
Viscosity @ 25°C		Thixotropic
Specific Gravity @ 25°C		1.1
Stability in the dark @ 20°C	months	3
Gel time @ 25°C using 2% Norox KP-9	minutes	6

Property		Fully cured *Gelcoat
Barcol Hardness (model GYZJ 934-1)		38
Water Absorption 24 hrs @ 23°C	mg	16
Deflection Temperature under load† (1.80 MPa)	°C	70
Elongation at Break	%	1.2
Tensile Strength	MPa	46
Tensile Modulus	MPa	5235

\*Curing Schedule - 24 hrs @ 20°C, 3 hrs @ 80°C

†Curing Schedule - 24 hrs @ 20°C, 5 hrs @ 80°C, 3 hrs @ 120°C

**Storage**

Crystic Gelcoat 44PA should be stored in the dark in suitable, closed containers. It is recommended that the storage temperature should be less than 20°C where practical, but should not exceed 30°C. Ideally, containers should be opened only immediately prior to use.

**Packaging**

Crystic Gelcoat 44PA is supplied in 25 kg and 225 kg containers.

**Health and Safety**

Please see separate Material Safety Data Sheets

Technical Leaflet No 102.22SA  
August 2013

Before you use this information, kindly verify that this data sheet is the latest version.

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

**SCOTT BADER COMPANY LIMITED**

Scott Bader (Pty) Ltd  
Reg. No. 93/00466/07  
1 Lubex Road,  
Hammasdale  
P.O. Box 1539, Hillcrest,  
3650. South Africa  
Tel: +27 (0) 31 736 8500  
Fax: +27 (0) 31 736 8511

Gauteng  
Broadacres Business  
Centre  
Cnr Cedar Rd and 3<sup>rd</sup>  
Ave  
Broadacres, Sandton  
Tel: (011) 064 5673

KwaZulu Natal  
1 Lubex Road,  
Hammasdale  
Tel: (031) 736 8500

Eastern Cape  
Freightpak Building  
Chevrolet St  
Markman Industrial  
Port Elizabeth  
Tel: (041) 409 783

Western Cape  
Unit 4B  
Tyger Lake  
Niagara Way  
Tyger Valley  
Cape Town  
Tel: (021) 914 6011

