

CRYSTIC[®] 625PA

Isophthalic Resin for Large Structures

Introduction

Crystic 625PA is an unsaturated isophthalic polyester resin supplied as a solution in monomeric styrene, which has been specially designed for the manufacture of large structures. Laminates made from this resin have excellent long-term water and weather resistance and their high rigidity and strength are retained at elevated temperatures up to 120°C. For marine applications where good heat resistance combined with long term water resistance are essential, e.g., GRP structures operating under load in tropical climates, Crystic 625PA can be used with confidence.

Formulation

Crystic[®] 625PA should be allowed to attain workshop temperature (18°C - 20°C) before use. Stir well by hand, or with a low shear mixer to avoid aeration, and then allow to stand to regain thixotropy. Crystic 625PA requires only the addition of a catalyst to start the curing reaction. The recommended catalyst is Norox[®] KP9, which should be added at 1% into the resin. Norox[®] MEKP-925H will increase the pot life. The catalyst should be thoroughly incorporated into the resin, with a low shear mechanical stirrer where possible. Crystic625PA is formulated for room temperature curing applications. It requires only addition of the correct amount of catalyst to start the curing reaction. The recommended formulations are given in Table 1:

Table 1

Component	Parts by weight
Crystic 625PA	100
Catalysts Norox KP9 or Norox MEKP-925H	1.0-3.0

Norox KP9 catalyst is suitable for general purpose use.

Norox MEKP-925H catalyst is recommended where extended pot life is required.

N.B. Peroxide catalysts are highly reactive and may decompose with explosive violence, or cause fires, if they come into contact with flammable materials, metals or accelerators. For this reason they must never be stored in metal containers or be mixed directly with accelerators.

The catalyst must be stirred thoroughly into the resin shortly before use. Curing should not be carried out at temperatures below 15°C. Scott Bader (Pty) Ltd. will not be liable for problems caused by use at lower temperatures than recommended. The resin must be allowed to attain workshop temperature (15-30°C) before being formulated for use.

Post Curing

Satisfactory laminates for many applications can be made from Crystic 625PA by curing at workshop temperature (20°C). However, in order to develop optimum heat and chemical resistance, laminates made with this resins must be post cured. After release from the mould, laminates should be allowed to mature for 24 hours at workshop temperature (20°C). They should then be post cured for a minimum of three hours at 80°C, or 15 hours at 50°C. When laminates are required to withstand temperatures between 50 and 100°C in service, the post-curing temperature should always be at least as high as that at which the laminate is required to operate. The post cure is most effective if it is carried out immediately after the 24 hour maturing period.

Chemical Resistance

Crystic 625PA is suitable for use in process engineering chemical environments and has equal properties to those of Crystic[®] 491PA. Performance figures for GRP laminates made with this resin in more than 200 different chemical environments are contained in Scott Bader Technical Leaflet No. 145.3, "Safe Chemical Containment", available on request.

Additive

Crystic 625PA can be pigmented with up to 5% Crystic Pigment Paste. Since the addition of certain pigments may affect the chemical resistant properties of laminates, users should seek advice from our Technical Service Department before making any additions.

Typical Properties

The following tables give typical properties of Crystic 625PA when tested in accordance with BS2782.

Table 3: Typical properties of liquid Crystic 625PA.

Property	Units	Nominal value
Appearance		cloudy mauvish
Viscosity @ 25°C 100 rpm, Brookfield RVT	centipoise	700
Thixotropic index	ratio	1.6
Specific gravity @ 25°C		1.13
Volatile Content	%	40
Stability in the dark at 20°C	months	3
Geltime @ 25°C using 1% Norox KP9 catalyst	minutes	20

Table 4: Typical properties of Crystic 625PA fully cured* resin (unfilled casting)

Property	Units	Nominal value
Barcol Hardness (GYZJ 934-1)		46
Deflection Temperature under load † (1.80 MPa)	°C	110
Water Absorption 24hrs @ 23°C	mg	20
Volumetric shrinkage	%	8
Tensile Strength	MPa	70
Tensile Modulus	MPa	3400
Elongation at Break	%	3.0

*Curing schedule - 24hrs @ 20°C, 3hrs @ 80°C

†Curing schedule - 24hrs @ 20°C, 5hrs @ 80°C, 3hrs @ 120°C

Storage

Crystic 625PA should be stored in the dark in suitable, closed containers. It is recommended that the storage temperature should be less than 20°C where practical, but should not exceed 30°C. Ideally, containers should be opened only immediately prior to use. Where they have to be stored outside, it is recommended that drums be kept in a horizontal position to avoid the possible ingress of water. Wherever possible, containers should be stored under cover.

Packaging

Crystic 625PA is supplied in 25kg kegs, 225kg drums, and 1125kg intermediate bulk containers. Bulk supplies can be delivered by road tanker.

Health and Safety

Please see the applicable Material Safety Data Sheets, depending on the curing system used.

Technical Leaflet No 102.22SA

August 2013

Before you use this information, kindly verify that this data sheet is the latest version.

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

SCOTT BADER COMPANY LIMITED

Scott Bader (Pty) Ltd
Reg. No. 93/00466/07
1 Lubex Road,
Hammarisdale
P.O. Box 1539, Hillcrest,
3650. South Africa
Tel: +27 (0) 31 736 8500
Fax: +27 (0) 31 736 8511

Gauteng
Broadacres Business
Centre
Cnr Cedar Rd and 3rd
Ave
Broadacres, Sandton
Tel: (011) 064 5673

KwaZulu Natal
1 Lubex Road,
Hammarisdale
Tel: (031) 736 8500

Eastern Cape
Freightpak Building
Chevrolet St
Markman Industrial
Port Elizabeth
Tel: (041) 409 783

Western Cape
Unit 4B
Tyger Lake
Niagara Way
Tyger Valley
Cape Town
Tel: (021) 914 6011

