



# CRESTAKYD<sup>®</sup> 44-5043

## Rosin / phenolic modified, short oil alkyd

### INTRODUCTION

CRESTAKYD 44-5043 is a linoleic/wood oil alkyd modified with both rosin and phenolic. It is supplied as a 60% non-volatile solution in xylene.

### CHARACTERISTICS

(Not to be taken as a specification)

Solids content		60
Oil type		Linoleic/wood
Solvent		Xylene
Acid Value (base resin)	mg KOH g <sup>-1</sup>	25 max
Colour	Gardner	10 max
Viscosity (25°C) (PRS bubble tube)	mPa·s	3250
Flash Point	°C	24

**APPLICATIONS**

CRESTAKYD 44-5043 has been designed for use in fast drying industrial primer applications.

**PACKAGING**

CRESTAKYD 44-5043 is supplied in drums. Bulk deliveries are by road tanker.

**STORAGE**

The resin should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 0°C and 30°C. Exposure to direct sunlight should be avoided.

**HEALTH & SAFETY**

Please see separate Material Safety Data Sheet.

Issue No.1

