

CRESTAKYD[®] 20-9021

Medium oil air drying alkyd

INTRODUCTION CRESTAKYD 20-9021 is a high viscosity chain stopped alkyd with excellent gloss, weathering resistance and flow characteristics.

CHARACTERISTICS (Not to be taken as a specification)

Appearance		Clear, bit free
Solids content	%	55
Oil type		linoleic
Oil content	%	49
Solvent		White Spirit : Xylene, 5.5:1
Acid value (base resin)	mg KOH g ⁻¹	10 max
Viscosity, Brookfield, Spindle 4, 10 rpm @ 25°C	mPa·s	12000
Viscosity, 40% NVC in White spirit DIN cup 4, @ 20°C	seconds	70 - 120
Colour	Gardner	6 max

APPLICATIONS

CRESTAKYD 20-9021 can be used for air drying primers and industrial finishes.

PACKAGING

CRESTAKYD 20-9021 can be supplied in drums. Bulk deliveries are by road tanker.

STORAGE

The resin should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 0°C and 30°C. Exposure to direct sunlight should be avoided.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No. 2

Scott Bader Company Limited
Wollaston, Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

