



TEXICRYL[®] 13-077

Provisional Data Sheet

INTRODUCTION TEXICRYL 13-077 is an APEO free modified styrene-acrylic copolymer emulsion.

CHARACTERISTICS (Not to be taken as a specification)

Solids Content	%	50
Viscosity at 25°C (Brookfield RVT, Spindle 2, 50 rpm)	mPa s	450
pH		8.5
Particle size	nm	180
Specific gravity at 25°C		1.10
Minimum film formation temperature*	°C	15

* Determined by metal bar with temperature gradient.

APPLICATIONS

TEXICRYL 13-077 is used in high performance flexible exterior coatings.

PACKAGING

TEXICRYL 13-077 is supplied in drums, 1 tonne IBC's or bulk supplies are delivered by road tanker.

STORAGE

TEXICRYL 13-077 may be stored in the containers in which it is supplied.

Protect from frost and extended exposure to direct sunlight.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No.1

Scott Bader Company Limited
Wollaston, Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

