



CRESTACRYL[®] 71-5060

Thermoplastic acrylic resin

INTRODUCTION

CRESTACRYL 71-5060 is a thermoplastic, pure acrylic resin which gives rapid solvent release, very good elasticity, excellent adhesion on metallic substrates and very good alkali and water resistance.

CHARACTERISTICS (Not to be taken as a specification)

Appearance		Clear, bit free
Solids Content	%	50
Solvent		Xylene
Viscosity at 40% solids in xylene Spindle 3, 10 rpm at 25°C	mPa·s	2250
Colour	Gardner	4 max
Glass transition temperature (midpoint)	°C	51
Viscosity as supplied Brookfield Spindle 6, 50 rpm at 25°C	mPa·s	17000

APPLICATIONS

CRESTACRYL 71-5060 can be used for various primers and finishes on metal and wood.

PACKAGING

CRESTACRYL 71-5060 can be supplied in drums. Bulk deliveries are by road tanker.

STORAGE

The resin should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 0°C and 30°C. Exposure to direct sunlight should be avoided.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No. 1

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

Scott Bader Company Limited, Wollaston,
Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100
Facsimile: +44 (0) 1933 666529



