

## CRESTACRYL<sup>®</sup> 71-8026

## Thermoplastic acrylic resin

| INTRODUCTION    | CRESTACRYL 71-8026 is thermoplastic acrylic designed for<br>use in fast drying roadmarking paints. The resin has excellent<br>hardness, combined with good elasticity and adhesion.    |                 |         |
|-----------------|--|-----------------|---------|
| CHARACTERISTICS | (Not to be taken as a specification)   |                 |         |
|                 | Appearance   | Clear, bit free |         |
|                 | Solids Content<br>60 min/125°C   | %               | 60      |
|                 | Solvent  |                 | Toluene |
|                 | Viscosity as supplied<br>Brookfield, Spindle 6, 50 rpm at 23°C   | mPa∙s           | 14500   |
|                 | Colour   | Gardner         | Max 4   |
|                 | Glass transition temperature (measured)  | °C              | 31      |
| APPLICATIONS    | CRESTACRYL 71-8026 is designed for use in formulating high grade road-marking paints.  |                 |         |
| PACKAGING       | CRESTACRYL 71-8026 can be supplied in drums. Bulk deliveries are by road tanker.   |                 |         |
| STORAGE         | The resin should be stored in the original unopened and<br>undamaged containers in a dry place at temperatures between<br>0°C and 30°C. Exposure to direct sunlight should be avoided. |                 |         |
| HEALTH & SAFETY | Please see separate Material Safety Data Sheet.  |                 |         |

Issue No. 4

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

Scott Bader Company Limited, Wollaston, Wellingborough, Northamptonshire, NN29 7RL Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

